

**SANTA MARGHERITA**

Società per Azioni  
Via del Marmo, 1098  
37020 VOLARGNE di Dolcè (Verona)  
CAP. SOC. € 3.088.670,00 int. vers.  
CODICE FISCALE 00828210237  
PARTITA IVA N. IT 00828210237  
C.C.I.A.A. VERONA: R.I. 00828210237 - R.E.A. VR 160754

37020 VOLARGNE (Verona) Italia - Tel. 045 6835888 - Telefax 045 6835800  
www.santamargherita.net - e-mail: info@santamargherita.net



**TrafficStone®**  
MADE IN ITALY

**Aosta**

cod: T513

## composition:

Engineered stone made quartz grits (93%) bound with polyester resin (7%)

**Standard size**

Slabs:	cm 305 x 140 x 1,2 cm 305 x 140 x 2 cm 305 x 140 x 3
Tiles:	cm 30 x 30 x 1,2 cm 40 x 40 x 1,2 cm 60 x 60 x 1,2
Skirting tiles:	cm 50 x 7 x 1

TECHNICAL DATA

**Technical Data**

TEST TYPE	Standard	Standard of measurement	TRAFFICSTONE
Water absorption	EN 14617 - 1	%	≤ 0,10
Density	EN 14617 - 1	kg/m <sup>3</sup>	2350 - 2450
Flexural strength module	EN 14617 - 2	MPa	30 - 60
Resistance to abrasion	EN 14617 - 4	mm	26 ± 3 mm
Shock resistance (thickness 20 mm)	EN 14617 - 9	joule	5±2
Chemical resistance	EN 14617 - 10	-	cl. C4
Thermal expansion	EN 14617 - 11	10 <sup>-6</sup> °C <sup>-1</sup>	< 30,0
Compression resistance	EN 14617 - 15	MPa	235 - 250
Moh's hardness	EN 101	Mohs	6 - 7
Resistance to fire	DIN 4102	-	B1
Slippage resistance	DIN 51130	-	honed 320 = R9